

# SPECIFICATIONS

## FR 701®

---

PATTERN	2100
CONTENTS	100% Terratex™ Polyester
WEIGHT	16.0 ± 0.5 Oz./Lin. Yd.
WIDTH	66" Useable
REPEAT	None

## CLEANING CODE

---

W-S	Fabric may be cleaned with mild, water-free solvents or water-based cleaning agents or foam.
-----	--

## PERFORMANCE

---


TENSILE (ASTM D 5034)	150 Lbs. Min. - Warp and Fill
TEAR (ASTM D 2261)	30 Lbs. Min. - Warp and Fill
MOISTURE REGAIN (ASTM D 2654)	0.5% Max.
COLORFASTNESS TO LIGHT (AATCC 16E)	40 Hrs.
COLORFASTNESS TO CROCKING (AATCC 8)	Class 4 Min. - Dry, Class 4 Min. - Wet

## FLAMMABILITY

---

ASTM E-84	Class 1 or A
NFPA-701 LARGE SCALE - 1989	Passes
STATE OF CA. TECH. BULLETIN 117 SEC. E (CS-191-53)	Passes

TERRATEX® IS A REGISTERED TRADEMARK OF INTERFACE INTERIOR FABRICS, INC. AND DESIGNATES FABRICS THAT ARE MADE FROM 100% RECYCLED MATERIAL USING INCREASINGLY SUSTAINABLE MANUFACTURING PRACTICES TO PRODUCE A HIGH QUALITY PRODUCT THAT IS RECYCLABLE AT THE END OF ITS USEFUL LIFE.

®  FR 701® IS INCLUDED IN THE UNDERWRITERS LABORATORY PANEL FABRIC RECOGNITION PROGRAM. ADDITIONAL TESTING OF THE U.L. RECOGNIZED COMPONENT FABRIC IS NOT REQUIRED ON APPROVED PANELS FROM PARTICIPATING MANUFACTURERS.

COLORS MAY VARY SLIGHTLY BETWEEN DYE LOTS.

APPLICATION TESTING OF THIS PRODUCT IS RECOMMENDED.

FR701® IS A REGISTERED TRADEMARK OF GUILFORD OF MAINE.

THIS SAMPLE IS REPRESENTATIVE OF THE FINISHED COLOR TO BE SUPPLIED AND MAY NOT INDICATE AN EXACT MATCH. WHILE EVERY EFFORT IS MADE TO MATCH THIS COLOR TO A MASTER SAMPLE, SOME VARIATION MAY OCCUR. WE DO NOT RECOMMEND THAT YOU SPECIFY FROM THIS CARD AND CANNOT BE RESPONSIBLE FOR VARIATIONS IN SHADE BETWEEN THIS PRINTED CARD AND ACTUAL FABRIC.

GUILFORD  
OF MAINE

GUILFORD OF MAINE  
5300 CORPORATE GROVE DR. SE  
SUITE 200  
GRAND RAPIDS, MI 49512-5512  
1 800 544 0200 FAX / 616 554 2255

GUILFORD OF MAINE (CANADA), INC.  
254 ST-URBAIN  
GRANBY, QUEBEC J2G 8M8  
CANADA  
450 777 3411 FAX / 450 777 3413

AN INTERFACE COMPANY

